

## TECHNICAL DATA SHEET

# EXTRA TILE ADHESIVE

### DESCRIPTION

High-quality, polymeric cementitious adhesive for absorbent and non-absorbent tiles. It does not slip. It is used to bond all kinds of tiles to surfaces where high adhesion, and moisture resistance are required. It can be used both indoors and outdoors. It is classified as C2T type according to EN 12004 and EN 12002.

### APPLICATION AREAS

**EXTRA** is suitable for gluing all types of ceramic tiles on walls and floors, on a wide variety of surfaces. Its use is recommended for large size tiles as well as natural stones (marble, granite). Ideal where high adhesion is required.

### APPLICATION INSTRUCTIONS

#### Surface preparation

The surface must be clean and free of loose spots, dust, paint, grease, oil and wetted before application.

#### Application

Empty the powder into a clean container with water at a ratio of 6.5 liters of water to 25 kg of adhesive. Stirring is done with a low-speed drill, until a homogeneous mass without lumps is created. The installation is done with a notched trowel, spreading the adhesive on the substrate. Then we comb the surface and place the tiles in the selected position, tapping them gently with a rubber mallet.

### CONSUMPTIONS

3-5kg/m<sup>2</sup>

### CLEANING

Clean the tools immediately after use with water.

### STORAGE

12 months from the date of production in unopened package kept in a dry place

### SAFETY

Read carefully the label of the product before use. Detailed instructions regarding hazards and safety are provided in the Safety Data Sheet, which is available upon request.

### PACKAGING

25kg paper bag/1200Kg pallet.

## TECHNICAL DATA SHEET

# EXTRA TILE ADHESIVE

### Technical Data:

Form	Cementitious powder	Slip (EN 1308)	≤0,5mm
Color	white	Application thickness	Up to 10mm
Open time	At least 30 min	Specific gravity of dry mortar	1,35±0.04Kg/L
Application temperature	From 5 °C to 35 °C	Pot life	5 hours
Consumption	3-5kg/m <sup>2</sup>	Water demand	6,5lt/25kg
Temperature resistance	From -40 °C to 90 °C	Wall grouting	4-8 hours
Adhesion strength after 28 days (EN 1348)	≥1,0 N/mm <sup>2</sup>	Floor grouting	24 hours
Adhesion strength after heating in +70°C (EN 1348)	≥1,0 N/mm <sup>2</sup>	Minor adjustments open time	10-15 min
Adhesion strength after immersion in water (EN 1348)	≥1,0 N/mm <sup>2</sup>	Packaging	25kg paper bag.
Adhesion strength after freeze-thaw cycles (EN 1348)	≥1,0 N/mm <sup>2</sup>		




## TECHNICAL DATA SHEET

# EXTRA TILE ADHESIVE

### NOTICE

The technical information and instructions provided in this datasheet referring to the application and end use of PROLAT products are based on the company's expertise and experience with the products to date. They are provided in good faith under the condition that the products are stored, used, and applied in accordance with PROLAT's instructions. However, given our inability to directly oversee conditions at construction sites or during product application, the company cannot guarantee the suitability of its products for specific purposes, nor does it assume any legal responsibility based on the information provided in this brochure, whether written, oral, or otherwise communicated. Users are advised to conduct a small test to assess the suitability of the products for their intended application and purpose of use. The company reserves the right to modify the properties of its products without prior notice.

 21	
<b>PROLAT S.A.</b> Production of Minerals and Mortars Afroditis 50 - P. Faliro, PC:175 61, Greece DoP No: 004-PROLAT-CPR	
EN 12004:2007+A1:2012 <b>EXTRA TILE ADHESIVE</b> NB: 0437 Improved cementitious adhesive with reduced slip, for internal and external tiling	
<b>Reaction to fire</b>	Class A1
<b>Release of dangerous substances</b>	See SDS
<b>Bond strength, as:</b>	
Initial tensile adhesion strength	≥ 1.0 N/mm <sup>2</sup>
<b>Durability, for:</b>	
Tensile adhesion strength after heat ageing	≥ 1.0 N/mm <sup>2</sup>
Tensile adhesion strength after water immersion	≥ 1.0 N/mm <sup>2</sup>
Tensile adhesion strength after freeze-thaw cycles	≥ 1.0 N/mm <sup>2</sup>