

TECHNICAL DATA SHEET

FINAL COAT PLASTER

DESCRIPTION

FINAL COAT PLASTER is a ready-to-use industrial mortar, based on high-strength Portland cement that only requires the addition of water. It contains specially selected aggregates of constant grain size. It contains hydraulic lime and special additives that give it excellent adhesion and very good workability.

Certified according to EN 998-1 and classified as type CS III, W0.

APPLICATION AREAS

FINAL COAT PLASTER is used after the basic layer of the classic plastering method, in an application thickness of 5 mm.

APPLICATION INSTRUCTIONS

Surface preparation

The surface must be clean and free of loose spots, dust, paint, grease, oil and wetted before application.

Application

Empty the powder (25kg) into a clean container with water (4.5-5lt) and stir with a low-speed drill (for a small amount) or with a concrete mixer (for a large amount). Stir until a homogeneous, lump-free mass is created. We apply the plaster with a trowel.

CONSUMPTION

Approximately 2 kg/m²/mm.

CLEANING

Clean the tools immediately after use with water.

STORAGE

12 months from the date of production in unopened package kept in a dry place

SAFETY

Read carefully the label of the product before use. Detailed instructions regarding hazards and safety are provided in the Safety Data Sheet, which is available upon request.

PACKAGING

25kg paper bag/1200Kg pallet.

TECHNICAL DATA SHEET

Revision No.v1
Revision Date: 06/2024

FINAL COAT PLASTER

Technical Data (Measurement conditions 23°C and 50% R.H.):

Form	cementitious powder	Coherence	177 mm
Water demand	4.5-5lt/25kg	Compressive strength	5,4 N/mm ²
Application temperature	from 5 °C to 35 °C	Adhesion strength (28 days)	0,6 N/mm ²
Consumption	2 kg /m ² /mm	Capillary water absorption	≤ 2,1 kg/m ² min ^{0,5}
Application thickness	5 mm	Water vapor permeability coefficient (μ)	49
Specific gravity of dry mortar	1630 Kg/m ³	Thermal conductivity (λ _{10,dry})	0,64 W/(m.K)
Specific gravity of wet mortar	1850 Kg/m ³	Reaction to fire	Class A1



TECHNICAL DATA SHEET

FINAL COAT PLASTER

NOTICE

The technical information and instructions provided in this datasheet referring to the application and end use of PROLAT products are based on the company's expertise and experience with the products to date. They are provided in good faith under the condition that the products are stored, used, and applied in accordance with PROLAT's instructions. However, given our inability to directly oversee conditions at construction sites or during product application, the company cannot guarantee the suitability of its products for specific purposes, nor does it assume any legal responsibility based on the information provided in this brochure, whether written, oral, or otherwise communicated. Users are advised to conduct a small test to assess the suitability of the products for their intended application and purpose of use. The company reserves the right to modify the properties of its products without prior notice.

 21
PROLAT S.A. Production of Minerals and Mortars Afroditis 50 - P. Faliro, PC:175 61, Greece DoP No: 009-PROLAT-CPR
EN 998-1:2016 ΣΟΒΑΣ ΤΕΛΙΚΗΣ ΣΤΡΩΣΗΣ General purpose rendering mortar (GP) for external and internal use Reaction to fire: Class A1 Adhesion: 0.5 N/mm ² – FP:A Water absorption: W0 Water vapor diffusion coeff.: μ:49 Thermal conductivity: (λ _{10,dry}) 0.64 W/mK (tab. value) Durability (against freeze/thaw): NPD Dangerous substances: See SDS