

TECHNICAL DATA SHEET**LAVACRYL STUCCO SPATULA****DESCRIPTION**

LAVACRYL STUCCO SPATULA is a ready-to-use general purpose pastry putty. It has good processability and is laid with typical ease. It sands very easily.

APPLICATION AREAS

It is ideal for troweling after grouting joints as well as for troweling entire surfaces (quality surface Q3 – Q4). Suitable for substrates such as plasterboard, plaster, concrete, aerated concrete.

APPLICATION INSTRUCTIONS**Surface preparation**

The surfaces must be dry, stable, smooth and clean. Dust, oil and glue residues must be cleaned before application.

Application

We mix the material and always use clean tools. The material has an excellent spreading. It hardens during the drying process. Because the duration of drying depends on weather conditions,

temperature and humidity, for any application in thicker layers we must take into account the ambient temperatures.

CONSUMPTION

Surface quality Q2, Q3, Q4: Approximately 1.4 kg/m²

CLEANING

Clean the tools immediately after use with water.

STORAGE

12 months from the date of production, protected against frost, high temperatures and exposure to direct sunlight

SAFETY

Read carefully the label of the product before use. Detailed instructions regarding hazards and safety are provided in the Safety Data Sheet, which is available upon request.

TECHNICAL DATA SHEET

LAVACRYL STUCCO SPATULA

Technical Data (Measurement conditions 23°C and 50% R.H.):

Form	pastry	Drying time	1-2 hours
Color	white	Recoat time	2-3 hours
Application temperature	from 10 °C to 35 °C	Flexural strength	300 N
Density	1.65 kg /cm ³		



TECHNICAL DATA SHEET

LAVACRYL STUCCO SPATULA

NOTICE

The technical information and instructions provided in this datasheet referring to the application and end use of PROLAT products are based on the company's expertise and experience with the products to date. They are provided in good faith under the condition that the products are stored, used, and applied in accordance with PROLAT's instructions. However, given our inability to directly oversee conditions at construction sites or during product application, the company cannot guarantee the suitability of its products for specific purposes, nor does it assume any legal responsibility based on the information provided in this brochure, whether written, oral, or otherwise communicated. Users are advised to conduct a small test to assess the suitability of the products for their intended application and purpose of use. The company reserves the right to modify the properties of its products without prior notice.

 24
PROLAT S.A. Production of Minerals and Mortars Afroditis 50 - P. Faliro, PC:175 61, Greece DoP No: 040-PROLAT-CPR
EN 13963:2005 LAVACRYL STUCCO SPATULA Type 3A Jointing Materials for Gypsum plasterboards Reaction to fire: Class F Flexural strength: 300 N